



UNIVERSITI PUTRA MALAYSIA

**RADIATION AND TEMPERATURE EFFECTS ON OPTICAL AND
ELECTRICAL PROPERTIES OF DYED POLY (VINYL ALCOHOL)
ORGANIC COMPOSITES CONTAINING CHLORINE**

SUSILAWATI

FPSK(P) 2005 6



**RADIATION AND TEMPERATURE EFFECTS ON OPTICAL AND
ELECTRICAL PROPERTIES OF DYED POLY (VINYL ALCOHOL)
ORGANIC COMPOSITES CONTAINING CHLORINE**

By

SUSILAWATI

**Thesis Submitted to the School of Graduate Studies,
Universiti Putra Malaysia, in Fulfillment of the Requirements
for the Degree of Doctor of Philosophy**

April 2005



DEDICATION

I dedicate this thesis special for my father Hj. Hambali, S.G B.A, my mother Hjh. Ahilmi, my husband Aris Doyan, PhD and my sons Muhammad Ikhsan, Ikhlasul Amal, and my late daughter Kurnia Ramadhani. I also dedicate this thesis to all my family.

Abstract of the thesis presented to the Senate of Universiti Putra Malaysia in fulfillment of requirement for the degree of Doctor of Philosophy

RADIATION AND TEMPERATURE EFFECTS ON OPTICAL AND ELECTRICAL PROPERTIES OF DYED POLY (VINYL ALCOHOL) ORGANIC COMPOSITES CONTAINING CHLORINE

By

SUSILAWATI

April 2005

Chairman: Associate Professor Elias Saion, PhD

Faculty: Science

The effects of radiation on dyed PVA-based organic blends containing chlorine have been studied for their potential applications in radiation dosimetry as well as in optical and electrochemical devices. The PVA-CH, PVA-TCA and PVA-TCE blends were doped with cresol red and blended separately with 23, 34, 45 and 57% CH and 20, 25, 30 and 35% TCA and TCE. The composite films were prepared by solvent-casting method and each film has been irradiated with γ -rays at different doses up to 12 kGy. The dosimetric and optical properties have been studied using Raman spectrometer and UV-VIS spectrophotometer in the wavelength range of 200 – 800 nm. The electrical properties have been studied using LCR meter, an impedance analyzer in the frequency range from 20 Hz to 1 MHz.



The dosimetric study has shown that the absorption spectra of the irradiated PVA-CH composite films change color from yellow to red, but for the irradiated PVA-TCA and PVA-TCE blends, the films change color from purple to yellow. The change in color is because of the lowering the pH in the films caused by the presence of acid generated by γ -ray interaction with CH, TCA and TCE. The useful critical dose at changing colour increases linearly with decreasing CH, TCA and TCE compositions in the range of (5.2 – 8.9), (5.0 – 7.5) and (6.0 – 8.7) kGy for PVA-CH, PVA-TCA and PVA-TCE respectively. The indirect dose response obtained from the absorbance at the absorption peaks has resulted in the linear increase of the dose sensitivity parameter D_0 with the increase of CH, TCA and TCE compositions. This has been confirmed by the direct dose response obtained from a decrease in the intensity of C-Cl bond of CH, TCA and TCE molecules due to radiation scission using Raman spectroscopy technique, which has resulted in the increase of D_0 with increasing CH, TCA and TCE compositions.

The optical absorption study has revealed that the absorption coefficient α increases with photon energy that is higher than the absorption edges with decreasing dose in range of (4.62 – 5.08), (4.00 – 4.74) and (4.44 – 4.88) eV for PVA-CH, PVA-TCA and PVA-TCE respectively for decreasing blend composition. The exponential relationship between the absorption coefficient and photon energy revealed that decreasing of Urbach's energy or optical activation energy ΔE with the increase of dose in the range of (0.69 – 0.64),

(0.68 – 0.61) and (0.72 – 0.65) eV for PVA-CH, PVA-TCA and PVA-TCE respectively for increasing blend composition. The direct band gap energy E_g obtained decreases with the increase of dose in the range of (4.12 – 4.02), (5.04 – 4.56) and (5.07 – 4.90) eV for PVA-CH, PVA-TCA and PVA-TCE respectively for increasing blend composition. While the indirect optical band gap energy E_g decreases with increasing dose in the range of (4.05 – 3.64), (3.8 – 3.44) and (4.62 – 4.23) eV for PVA-CH, PVA-TCA and PVA-TCE respectively for increasing blend composition. These changes are attributed to the radiation effect on the optical transitions of electrons from donor atoms to acceptor atoms in the electronic structure of the composites.

The conductivity-dose relation study revealed that increase in conductivity of the irradiated PVA-CH, PVA-TCA and PVA-TCE blends with increasing dose up to 12 kGy. The increase in the conductivity with dose is attributed to the increase of ionic carriers in the composites induced by radiation scission of CH, TCA and TCE molecules and also due to hydrolysis of water. The conductivity spectra consist of frequency-independent dc component and frequency-dependent ac component. The flat response of dc conductivity has been attributed to free ions and has Arrhenius type relationship with dose that resulted in dose sensitivity D_0 increases with increasing blend composition. The power law type response of ac conductivity has been attributed to hopping of ions trapped in the localized sites of the PVA matrix and resulted in frequency exponent s decreases with increasing blend

composition. The conductivity-temperature relation study revealed that an increase conductivity of the unirradiated PVA-CH, PVA-TCA and PVA-TCE blends with increasing temperature up to 353 K. The increase of conductivity with temperature is attributed to the increase of free ion mobility due to thermal energy kT and possible more ions gained kinetic energy via the thermally activated hopping of charge carriers between trapping sites and phonon-assisted quantum tunneling through a barrier separating two equilibrium positions. The conductivity activation energy obtained decreases with the blend composition increases.

The dielectric-dose relation study revealed that an increase of the dielectric constant ϵ' of the composites with increasing dose, which is attributed to the orientation polarizations of dipoles in the polymer system. The increase in dielectric loss ϵ'' with increasing dose can be attributed to dielectric dipole relaxation and dc conductivity of free ions in the blends. The dose sensitivity D_0 obtained increases with increasing blend composition. The dielectric-temperature relation study revealed that an increase of the dielectric constant ϵ' with temperature can be attributed to the increase in the ability of dipoles to rotate towards the applied field as the binding forces between ions and atoms become weak with increasing temperature in the so called free volume effect. The increase in ϵ'' value with temperature increase can be attributed to the dc conduction process where the charge carriers gained kinetic energy via the thermal energy kT , thus increase the mobility of the

free ions and the dielectric loss value. The electric activation energy obtained decreases with the blend composition increases.

Abstrak tesis yang dikemukakan kepada Senat Universiti Putra Malaysia
bagi memenuhi keperluan untuk ijazah Doktor Falsafah

**KESAN SINARAN DAN SUHU KE ATAS SIFAT OPTIK DAN
ELEKTRIK BAGI POLY (VINYL ALKOHOL) BERPERWARNA
MENGANDUNGI SEBATIAN ORGANAN BERKLORIN**

Oleh

SUSILAWATI

April 2005

Pengerusi: Profesor Madya Elias Saion, PhD

Fakulti : Sains

Kesan sinaran terhadap campuran polimer berasaskan PVA berperwarna yang mengandungi sebatian organan berklorin telah diselidiki untuk menunjukkan keupayaan aplikasinya dalam dosimetri sinaran dan peranti optik dan elektrokimia. Komposit PVA-CH, PVA-TCA dan PVA-TCE telah didopkan dengan perwarna cresol merah dan dicampurkan secara berasingan dengan sebatian organan pada komposisi 23, 34, 45 and 57% CH dan 20, 25, 30 and 35% TCA dan TCE. Film komposit disediakan dengan kaedah kimia acuan pelarut dan setiap film itu telah disinarkan dengan sinar- γ pada dos yang berbeza sehingga 12 kGy. Pengkajian sifat-sifat dosimetri dan optik telah diselidiki dengan menggunakan kaedah spektroskopi Raman dan spektrofotometer UV-VIS dalam julat panjang gelombang 200 - 800 nm. Pengkajian sifat-sifat elektrik pula telah diselidik

dengan menggunakan meter LCR, melibatkan analisis impedans dalam julat frekuensi daripada 20 Hz hingga 1 MHz.

Pengkajian dosimetri menunjukkan bahawa spektra penyerapan film PVA-CH tersinar telah berubah daripada warna kuning kepada warna merah, sedangkan bagi film PVA-TCA dan PVA-TCE tersinar perubahan berlaku daripada warna ungu kepada warna kuning. Perubahan warna ini disebabkan penurunan pH dalam yang tersebut dihasilkan oleh pertambahan asid kerana tindakan sinar- γ dengan sebatian CH, TCA dan TCE. Didapati bahawa dos kritikal di mana berlaku pertukaran warna akan berkurangan secara linear dengan pertambahan komposisi CH, TCA dan TCE iaitu dalam julat (5.2 – 8.9), (7.5 – 5) dan (8.7 – 6) kGy untuk masing-masing PVA-CH, PVA-TCA dan PVA-TCE. Sambutan dos secara tak terus didapati daripada penyerapan pada puncak penyerapan dan menghasilkan parameter dos kepekaan D_0 , yang bertambah secara linear dengan komposisi CH, TCA and TCE. Ini telah disahkan dengan kaedah sambutan dos secara terus yang diperolehi daripada pengurangan keamatan ikatan C-Cl bagi CH, TCA dan TCE kerana tindakan sinar- γ secara kaedah spektroskopi Raman yang juga menghasilkan parameter dos kepekaan D_0 yang bertambah dengan komposisi CH, TCA and TCE.

Pengkajian sifat optik menunjukkan bahawa pekali penyerapan α bertambah dengan pertambahan tenaga foton yang melebihi tenaga sisi penyerapan

dengan pengurangan nilai dos dalam julat (4.62 – 5.08), (4.00 – 4.74) dan (4.44 – 4.88) eV bagi masing-masing PVA-CH, PVA-TCA dan PVA-TCE untuk komposisi berkurang. Hubungan bereksponen antara pekali penyerapan dan tenaga foton telah menunjukkan bahawa tenaga Urbach atau tenaga pengaktifan optik berkurangan dengan pertambahan dos dalam julat (0.69 – 0.64), (0.68 – 0.61) and (0.72 – 0.65) eV bagi masing-masing PVA-CH, PVA-TCA and PVA-TCE untuk komposisi yang bertambah. Jurang tenaga terus E_g berkurangan dengan penambahan dos dalam julat (4.17 – 4.02), (5.04 – 4.56) and (5.07 – 4.90) eV bagi masing-masing komposit PVA-CH, PVA-TCA dan PVA-TCE untuk komposisi yang bertambah. Manakala jurang tenaga takterus E_g berkurangan dengan pertambahan dos dalam julat (4.05 – 3.64), (3.8 – 3.44) and (4.62 – 4.23) eV bagi masing-masing PVA-CH, PVA-TCA dan PVA-TCE untuk komposisi yang bertambah. Perubahan ini disebabkan oleh kesan sinaran terhadap peralihan optik bagi electron dari atom penderma ke atom penerima bagi struktur elektronik komposit tersebut.

Pengkajian tentang hubungan kekonduksian-dos menunjukkan bahawa penambahan kekonduksian PVA-CH, PVA-TCA dan PVA-TCE tersinar dengan penambahan dos sehingga kepada 12 kGy. Penambahan kekonduksian elektrik disebabkan oleh penambahan pembawa ion yang diinduksikan oleh pemecahan ikatan molekul sebatian CH, TCA dan TCE oleh sinaran dan juga oleh ion hasil daripada hidrolisis air. Spektra kekonduksian terdiri daripada komponen arus terus (a.t) yang tak bersandar

kepada frekuensi dan komponen arus ulang-alik (a.u) yang bersandar kepada frekuensi. Sambutan kekonduksian a.t yang mendatar adalah disebabkan oleh ion-ion bebas dan mempunyai hubungan jenis Arrhenius yang menghasilkan parameter dos kepekaan D_0 bertambah dengan peningkatan komposisi campuran. Sambutan jenis hukum kuasa bagi kekonduksian a.u pula disebabkan oleh mekanisma loncatan (hopping) ion-ion antara kedudukan setempat bagi ion-ion yang terperangkap dalam polimer matrik PVA yang menghasilkan eksponen frekuensi s berkurangan dengan peningkatan komposisi. Pengkajian tentang hubungan kekonduksian-suhu menunjukkan bahawa penambahan kekonduksian komposit PVA-CH, PVA-TCA dan PVA-TCE tak tersinar kepada suhu sehingga 353 K. Penambahan kekonduksian dengan suhu disebabkan pertambahan kelincahan ion bebas setelah menerima tenaga terma kT dan kemungkinan juga oleh banyak ion menambahkan tenaga kinetik melalui mekanisma lompatan pembawa cas antara kedudukan-kedudukan terhalang dan juga oleh terowong terkuantum dengan bantuan fonon melalui satu hadangan yang memisahkan antara dua kedudukan keseimbangan. Tenaga pengaktifan kekonduksian yang dihasilkan berkurangan nilainya dengan komposisi yang bertambah.

Pengkajian tentang hubungan dielektrik-dos menunjukkan bahawa penambahan pemalar dielektrik ϵ' dengan peningkatan dos kerana orientasi pengutupan dalam sistem polimer. Penambahan lesapan dielektrik ϵ'' pula

disebabkan oleh saintaian dwikutub dan kekonduksian a.t bagi ion bebas dalam komposit tersebut. Parameter dos kepekaan D_0 yang dihasilkan bertambah dengan komposisi campuran. Pengkajian tentang hubungan dielektrik-suhu menunjukkan bahawa penambahan pemalar dielektrik ϵ' dengan peningkatan suhu disebabkan oleh keupayaan dwikutub untuk berputar ke arah medan kerana ikatan daya antara ion-ion dan atom-atom bertambah longgar kerana kesan isipadu bebas bertambah dengan suhu. Penambahan lesapan dielektrik ϵ'' dengan suhu pula disebabkan oleh proses kekonduksian a.t yang mana pembawa cas meningkatkan tenaga kinetik melalui tenaga terma kT dan dengan demikian menambahkan kelincahan ion bebas dan menambahkan nilai lesapan dielektrik. Tenaga pengaktifan elektrik yang dihasilkan berkurangan nilainya dengan komposisi yang bertambah.

ACKNOWLEDGEMENTS

I would like to express my utmost gratitude to the Associate Prof. Dr Elias Saion, Chairman of the Supervisory Committee and to the other members of the Committee, namely Prof. Dr. Khaida Khalid, Associate Prof. Dr. Wan Mohd. Daud Wan Yusoff, Associate Prof. Dr. Mohammad Zaki Ab. Rahman and Dr. Khairul Zaman M. Dahlan for their extremely invaluable guidance, meticulous discussions, positive criticism and continuous encouragement throughout my studies.

I would like to express my words of thanks to the government of Malaysia for supporting my research by IRPA Grant (No. 09-02-04-0275-EA001).

I am grateful to the government of Indonesia for providing partial travel allowance, and granting me deputation to complete this study.

I would also like to acknowledge the assistance provided to me by the staff of the Department of Physics, namely Mr. Mohammad Zain, Mr. Razak, Mr. Ruslim, Mr. Rahmat and all lecturers.

Thanks are expressed to the Malaysian Institute for Nuclear Technology Research (MINT) for allowing me to irradiate my samples. I extend my words of thanks to the SDDL staff, namely Mr. Taiman Kadni, M.Sc and Mr. Hasan Hisam.



It will be awful for me if I forget to express my sincere thanks to my friends and co-research fellows of our research group, namely, Mr. Charles Walter, Msts. Azian Othman and Azlina Baha. Finally, I would like to thank my father Hambali and my mother Ahilmi, my mother in-law, my husband Aris Doyan, my sons Muhammad Ikhsan, Ikhlasul Amal, my late daughter Kurnia Ramadhani and also to all my family for their patience, inspiration and understanding.

I certify that an Examination Committee met on 1st April 2005 to conduct the final examination of Susilawati on her Doctor of Philosophy thesis entitled "Radiation and Temperature Effects on Optical and Electrical Properties of Dyed Poly (Vinyl Alcohol) Organic Composites Containing Chlorine" in accordance with Universiti Pertanian Malaysia (Higher Degree) Act 1980 and Universiti Pertanian Malaysia (Higher Degree) Regulations 1981. The Committee recommends that the candidate be awarded the relevant degree. Members of the Examination Committee are as follows:

Mohd. Maarof H.A. Moksini, PhD

Professor

Faculty of Science

Universiti Putra Malaysia

(Chairman)

Abdul Halim Shaari, PhD

Professor

Faculty of Science

Universiti Putra Malaysia

(Internal Examiner)

Zainal Abidin Talib, PhD

Associate Professor

Faculty of Science

Universiti Putra Malaysia

(Internal Examiner)

Ahmad Termizi Ramli, PhD

Professor

Faculty of Science

Universiti Teknologi Malaysia

(External Examiner)



GULAM RUSUL RAHMAT ALI, PhD

Professor/Deputy Dean

School of Graduate Studies

Universiti Putra Malaysia

Date: 19 MAY 2005

This thesis submitted to the Senate of Universiti Putra Malaysia and has been accepted as fulfillment of the requirement for the degree of Doctor of Philosophy. The members of the Supervisory Committee are as follows:

Elias Saion, PhD

Associate Professor
Faculty of Science
Universiti Putra Malaysia
(Chairman)

Khaida Khalid, PhD

Professor
Faculty of Science
Universiti Putra Malaysia
(Member)

Wan Daud Wan Yussof, PhD

Associate Professor
Faculty of Science
Universiti Putra Malaysia
(Member)

Zaki Abd Rahman, PhD

Associate Professor
Faculty of Science
Universiti Putra Malaysia
(Member)

Kamaruzzaman Hj Dahlan, PhD

MINTS Bangi
(Member)



AINI IDERIS, PhD

Professor/Dean
School of Graduate Studies
Universiti Putra Malaysia

Date: 09 JUN 2005

DECLARATION

I hereby declare that the thesis is based on my original work except for quotations and citations, which have been duly acknowledged. I also declare that it has not been previously or concurrently submitted for any other degree at UPM or other institutions.



SUSILAWATI

Date: 18 mei 2005

TABLE OF CONTENTS

	Page
DEDICATION	ii
ABSTRACT	iii
ABSTRAK	viii
ACKNOWLEDGEMENTS	xiii
APPROVAL	xv
DECLARATION	xvii
LIST OF TABLES	xxiii
LIST OF FIGURES	xxv
LIST OF ABBREVIATIONS	xxxviii

CHAPTER

I	INTRODUCTION	1
II	LITERATURE REVIEW	12
	Introduction	12
	Radiation Processing	13
	Gamma irradiators	14
	Electron accelerators	15
	Chemistry of Radiation Processing	16
	Materials Modification	17
	Dosimetry of Radiation Processing	19
	Interaction of Light in Solid Composite Polymers	24
	Light Absorbance in Irradiated SCPs	24
	Optical Absorption of Irradiated SCPs	32
	Raman Scattering of Irradiated SCPs	37
	Interaction of Electromagnetic Field in Solid Composite Polymers	40
	Electrical Conductivity of Irradiated SCPs	40
	Dielectric Properties of Irradiated SCPs	42
III	THEORETICAL WORKS	48
	Interaction of Ionizing radiation with Matter	48
	Ionizing Radiations	48
	Gamma Ray Source	49
	Gamma Ray Interactions	51
	Photoelectric effect	53



	Rayleigh scattering	54
	Compton scattering	55
	Pair production	56
	Absorbed dose	57
	Molecular Absorption Spectroscopy	58
	Electromagnetic Fields in Matter	58
	Properties of Light	59
	Molecular Spectroscopy	60
	Optical Absorption	63
	Beer-Lambert Law	67
	Absorption process	68
	Absorption edge	71
	The exponential region of the absorption edge	72
	High absorption region	73
	Allowed direct transitions	73
	Indirect transition between indirect valleys	74
	Indirect transition between direct valleys	76
	Classical theory of Raman Scattering:	77
	Molecular Polarisability	
	Quantum Theory of Raman Scattering	84
	Interaction of Electromagnetic Fields with Dielectrics	88
	Dielectrics	88
	Polarization in dielectrics	91
	Relaxation Time and Debye Equation	94
	Complex Electric Modulus	98
	Electrical Conduction in Dielectrics	99
IV	SAMPLE PREPARATION AND CHARACTERIZATIONS	104
	Sample Preparation	104
	Preparation of stock solution of cresl red dye	104
	Preparation of Dyed PVA composite films	104
	Gamma Irradiation	106
	UV-VIS Absorption Spectra Measurements	110
	UV-VIS absorption spectrophotometer	110
	Continuous Illumination Light Sources	112
	Pulsed Illumination Light Sources	112
	Optical Absorption Spectra Measurement	113
	Raman Scattering Spectra Measurement	114
	Electrical Characteristic Measurements	118
	Impedance Analyzer, HP 4284A LCR meter	118
	Conductivity and Dielectric Measurements	120

V	EFFECTS OF RADIATION ON DOSIMETRIC AND OPTICAL PROPERTIES	122
	Introduction	122
	PVA-CH Composites	124
	Absorption Spectra	124
	Formation of Acid in PVA-CH Composites	129
	Critical Dose at Color Change	132
	Absorption Spectra Dose Response	136
	Raman Spectra Dose Response	199
	Absorption Edge	145
	Activation energy	149
	Band Gap Energy	153
	PVA-TCA Composites	162
	Absorption Spectra	162
	Formation of Acid in PVA-TCA Composites	165
	Critical Dose at Color Change	167
	Absorption Spectra Dose Response	170
	Raman Scattering Dose Response	172
	Absorption Edge	175
	Activation energy	179
	Band Gap Energy	182
	PVA-TCE Composites	189
	Absorption Spectra	189
	Formation of Acid in PVA-TCE Composites	192
	Critical Dose at Color Change	194
	Optical Absorption Dose Response	198
	Raman Spectra Dose Response	201
	Absorption Edge	204
	Activation energy	207
	Band Gap Energy	210
VI	EFFECTS OF RADIATION AND TEMPERATURE ON ELECTRICAL CONDUCTIVITY	217
	Introduction	217
	PVA-CH composites	219
	Dose-Dependent AC Conductivity	219
	Frequency Exponent	224
	Hopping Frequency	228
	Impedance	231
	Dose-Dependent DC Conductivity and Dose Sensitivity	234
	Temperature-Dependent AC conductivity	237
	Frequency Exponent	241
	Hopping Frequency	244

	Impedance	246
	Temperature-Dependent DC Conductivity and Activation Energy	249
	PVA-TCA composites	255
	Dose-Dependent AC Conductivity	255
	Frequency Exponent	258
	Hopping Frequency	262
	Impedance	264
	Dose-Dependent DC Conductivity and Dose Sensitivity	267
	Temperature-Dependent AC conductivity	269
	Frequency Exponent	273
	Hopping Frequency	276
	Impedance	278
	Temperature-Dependent DC Conductivity and Activation Energy	281
	PVA-TCE composites	287
	Dose-Dependent AC Conductivity	287
	Frequency Exponent	290
	Hopping Frequency	294
	Impedance	297
	Dose-Dependent DC Conductivity and Dose Sensitivity	299
	Temperature-Dependent AC conductivity	301
	Frequency Exponent	305
	Hopping Frequency	308
	Impedance	310
	Temperature-Dependent DC Conductivity and Activation Energy	312
VII	EFFECTS OF RADIATION AND TEMPERATURE ON DIELECTRIC PERMITTIVITY	318
	Introduction	318
	PVA-CH Composites	320
	Dose-Dependent of Dielectric Permittivity	320
	Response Model of Dielectric Constant and Dielectric Loss	328
	Complex Electric Modulus	335
	Dose-dependent Electric Relaxation and Dose Sensitivity	340
	Temperature-Dependent Dielectric Permittivity	343
	Response Model of Dielectric Constant and Dielectric Loss	349

Complex Electric Modulus	355
Temperature-Dependent Electric Relaxation and Activation Energy	359
PVA-TCA Composites	363
Dose-Dependent of Dielectric Permittivity	363
Response Model of Dielectric Constant and Dielectric Loss	368
Complex Electric Modulus	374
Dose-dependent Electric Relaxation and Dose Sensitivity	378
Temperature-Dependent Dielectric Permittivity	381
Response Model of Dielectric Constant and Dielectric Loss	386
Complex Electric Modulus	392
Temperature-Dependent Electric Relaxation and Activation Dose	396
PVA-TCE Composites	399
Dose-Dependent of Dielectric Permittivity	399
Response Model of Dielectric Constant and Dielectric Loss	405
Complex Electric Modulus	411
Dose-dependent Electric Relaxation and Dose Sensitivity	415
Temperature-Dependent Dielectric Permittivity	418
Response Model of Dielectric Constant and Dielectric Loss	423
Complex Electric Modulus	429
Temperature-Dependent Electric Relaxation and Activation Energy	433
VIII CONCLUSIONS	436
Suggestions for Future Research	445
REFERENCES	447
APPENDICES	465
BIODATA OF THE AUTHOR	470
PUBLICATIONS FROM THIS WORK	471

LIST OF TABLES

Table		Page
2.1	Chemical composition and physical parameters used by different workers for the optical study of films dosimeter	31
2.2	Optical property studies of polymers and compounds with and without treatment of ionizing radiations	36
2.3	Component and physical parameters used by different workers for the Raman spectroscopy study of polymers	40
2.4	Chemical composition and physical parameters used by different workers for dielectric and conductivity study of polymer films	45
6.1	The values of hopping frequency (Hz) ω_p at various doses and CH compositions	229
6.2	The values of hopping frequency (Hz) ω_p at various temperatures and CH compositions	244
6.3	The values of hopping frequency (Hz) ω_p at various doses and TCA compositions	262
6.4	The values of hopping frequency (Hz) ω_p at various temperatures and TCA compositions	277
6.5	The values of hopping frequency (Hz) ω_p at various doses and TCE compositions	295
6.6	The values of hopping frequency (Hz) ω_p at various temperatures and TCE compositions	308
7.1	Characterization of the dispersion data for PVA-CH composites at 23, 34, 45 and 57% of CH for different doses	330
7.2	Characterization of the dispersion data for PVA-CH composites at 23, 34, 45 and 57% of CH for different temperature	350



7.3	Characterization of the dispersion data for PVA-TCA composites at 20, 25, 30 and 35% of TCA for different doses	369
7.4	Characterization of the dispersion data for PVA-TCA composites at 20, 25, 30 and 35% of TCA for different temperature	387
7.5	Characterization of the dispersion data for PVA-TCE composites at 20, 25, 30 and 35% of TCE for different doses	406
7.6	Characterization of the dispersion data for PVA-TCE composites at 20, 25, 30 and 35% of TCE for different temperature	424